



Linear Low Density Polyethylene

LL0640AA / LL0640KJ

Typical properties	Test method (ASTM)	Unit	Value
MFI@190°C,2.16 kg	D1238	gr/10min	4
Density	D2839	gr/ml	0.929
Tensile Strength@Yield ,MD/TD	D638	Mpa	12/12
Elongation@Break,MD/TD	D638	%	600/810
Tensile Strength@Break,MD/TD	D688	Mpa	33/25
Haze	D1003	%	2
Gloss(45°)	D2457	Rating	87

➤ Values shown are averages & are not to be considered as product specifications.

* 40 microns, Film Cast at 75 m/min,240°C

MD=Machine Direction, TD=Transverse Direction

❖ Main application & Characteristics:

LL0640AA & LL0640KJ are linear low density polyethylene copolymers containing butene-1 as a co-monomer.

LL0640AA & LL0640KJ have been specially designed for the production of high quality cast films, such as display packaging, bubble film and non cling layer for stretch film.

LL0640AA & LL0640KJ have the following advantages:

- High melt flow rate for high output cast extrusion.
- Excellent combination of strengths and stiffness.
- High gloss and clarity.

If corona treatment is necessary, the level should normally be in the range 38-48 mN/m.

Melt temperature range in the cast process are normally 220°C-260°C and in lean blends for blown film are 160°C-215°C.

LL0640AA & LL0640KJ should be stored in the dry condition below the 50°C and avoided from the exposure of direct sunlight.

* LL0640AA & LL0640KJ are suitable for food contact.

1473 SK NO:5
Muzaffer Tuzcuoğlu
Business Center
Alsancak
İZMİR, TURKEY

+90 544 317 84 64

+90 553 546 50 56

www.aypetkim.com.tr

info@aypetkim.com.tr